

CEL-SPAN® Purge 388



Cel-Span® Purge 388

Most versatile and widely used in the plastics industry.

Cel-Span® Purge 388 is a transition purge that contains several proprietary additives that are essential in the cleansing cycle of high temperatures and lower melting polyolefins. Temperatures above 500 °F may cause material to smoke. Cel-Span® Purge 388 can be used directly without any mixing necessary to clean most plastic equipment during color and resin changes. The unique additives and resin system in Cel-Span® Purge 388 makes it possible to cleanse color resins in less time, in most resin applications.

Applications: Injection Molding – Blow Molding – Pipe/Profile Sheet

Temperature Range: 350°F – 500°F (177°C – 260°C)

Melt Flow: 1-10 HLMI (grams/10 min.), at 190°C/21.6kg

Blend Density: 0.955 g/cc

Types of Resins: PE, PP, PS, PA,

Amount Required: 1 – 3 times barrel capacities suggested, but actual amount depends on machine conditions

Features and Benefits:

- Easy to use
- No process changes needed
- Use at the normal resin processing temperature and RPM speed
- Safe, non-hazardous materials with FDA compliance
- No mixing required
- One year shelf life
- Not just a mechanical purge

Cel-Span® Purge 388 has been one of the industry's best performing purging compounds for 15 years! Our purging compounds and additives offer superior cleansing and economic value over in-house methods and other commercial purges. Cel-Span® Purge 388 is packaged in 55 lb. bags or 1,100 lb. gaylord boxes. We recommend this product be kept closed and stored in the original container, away from light, heat, and highly humid environments.

Disclaimer - This data contains general information and describes typical properties only. Only persons qualified to determine for themselves the suitability of our products for particular purposes should evaluate its potential uses. No guarantee is made or liability assumed, the application of this data and the products described herein being at the sole risk of the user. Samples are provided to the requestor on an "AS IS, WHERE IS" evaluation purpose only basis, solely under the use and direction of the requestor, without warranty of any kind (either express or implied), including but not limited to any implied warranties of merchantability and fitness for a specific or general purpose and those arising by statute or by law, or from a cause of dealing or usage of trade. In no event, regardless of cause, shall Phoenix Plastics be liable for any indirect, special, incidental, punitive or consequential damages of any kind, whether arising under breach of contract, tort (including negligence), strict liability or otherwise, and whether based on this agreement or otherwise, even if advised of the possibility of such damages.

5400 Jefferson Chemical Road • Conroe, Texas 77301 • Office 1-866-760-2311 - Fax (936) 760-2322 • www.phoenixplastics.com