

CEL-SPAN® S 100



Cel-Span® S 100

A stabilizing and dispersant aid for color in extrusion and film applications.

Cel-Span® S 100 is a compounded additive for color stabilization and dispersion. A unique proprietary compounding technique makes it possible to pelletize the entire active stabilizer and dispersant in the formulation without adding additional heat history. Cel-Span® S 100 should be utilized at 0.25% to 1% consistently during the color concentration manufacturing processes for stabilization and dispersion. Cel-Span® S 100 also lessens degradation of pigments and enhances the brightness of color concentrates. The pigment is initially dispersed by dispersing agents in order to prevent the formation of uncontrolled flocculates; a process of contact and adhesion whereby the particles of dispersion form larger-size clusters. Stability of dispersion is a result of interplay of the heat (kinetic) energy of particles, attractive inter-particle forces, and repulsive forces; this also helps to limit short-range Van der Waals forces.

Applications: Extrusion - Compounding

Melt point: 157°F (69.6°C)

Blend Density: 0.925 g/cm³ (32 lb. /ft³)

Types of Resins: Polyolefin

Amount Required: 0.25% - 1%

Features and Benefits:

- Low dosages
- Enhances color
- Increases physical integrity of the polymer

Cel-Span® S 100 is packaged in 50 lb. bags or 1,000 lb. gaylord boxes. We recommend this product be kept closed and stored in the original container, away from light, heat, and highly humid environments. Cel-Span® S 100, once blended, should be processed and not stored for future use. Opened packages should be closed tightly to limit oxygen permeation and oxidation of stabilizing and other hygroscopic additives. No adverse health effects from the use of Cel-Span® S 100 are known. All additives in this unique formulation are GRAS and FDA compliant for food contact.

Disclaimer - This data contains general information and describes typical properties only. Only persons qualified to determine for themselves the suitability of our products for particular purposes should evaluate its potential uses. No guarantee is made or liability assumed, the application of this data and the products described herein being at the sole risk of the user. Samples are provided to the requestor on an "AS IS, WHERE IS" evaluation purpose only basis, solely under the use and direction of the requestor, without warranty of any kind (either express or implied), including but not limited to any implied warranties of merchantability and fitness for a specific or general purpose and those arising by statute or by law, or from a cause of dealing or usage of trade. In no event, regardless of cause, shall Phoenix Plastics be liable for any indirect, special, incidental, punitive or consequential damages of any kind, whether arising under breach of contract, tort (including negligence), strict liability or otherwise, and whether based on this agreement or otherwise, even if advised of the possibility of such damages.